



INTERNATIONAL STANDARD ISO 17615:2007
TECHNICAL CORRIGENDUM 1

Published 2008-03-01

INTERNATIONAL ORGANIZATION FOR STANDARDIZATION • МЕЖДУНАРОДНАЯ ОРГАНИЗАЦИЯ ПО СТАНДАРТИЗАЦИИ • ORGANISATION INTERNATIONALE DE NORMALISATION

Aluminium and aluminium alloys — Alloyed ingots for remelting — Specifications

TECHNICAL CORRIGENDUM 1

Aluminium et alliages d'aluminium — Lingots pour refusion en aluminium allié — Spécifications

RECTIFICATIF TECHNIQUE 1

Technical Corrigendum 1 to ISO 17615:2007 was prepared by Technical Committee ISO/TC 79, *Light metals and their alloys*, Subcommittee SC 7, *Aluminium and cast aluminium alloys*.

Page 8

Replace the first 7 columns in the last line of Table 1 with the following text.

Al ZnSiMg	Al Zn10Si8Mg	7,7 to 8,3 (7,5 to 9,0)	0,27 (0,30)	0,08 (0,10)	0,10 (0,15)	0,25 to 0,4 (0,2 to 0,4)
-----------	--------------	----------------------------	----------------	----------------	----------------	-----------------------------

Pour plus d'infos, merci de nous contacter.

Association Sénégalaise de Normalisation

4 Avenue Jean Jaurès, Immeuble El Hadj Omar DIA, 6 ème Etage
Dakar - SENEGAL

Tel: +221 33 829 58 25

Email: asn@asn.sn