



INTERNATIONAL STANDARD ISO 105-A02:1993 TECHNICAL CORRIGENDUM 2

Published 2005-10-01

INTERNATIONAL ORGANIZATION FOR STANDARDIZATION • МЕЖДУНАРОДНАЯ ОРГАНИЗАЦИЯ ПО СТАНДАРТИЗАЦИИ • ORGANISATION INTERNATIONALE DE NORMALISATION

Textiles — Tests for colour fastness — Part A02: Grey scale for assessing change in colour

TECHNICAL CORRIGENDUM 2

Textiles — Essais de solidité des teintures —

Partie A02: Échelle de gris pour l'évaluation des dégradations

RECTIFICATIF TECHNIQUE 2

Technical Corrigendum 2 to ISO 105-A02:1993 was prepared by Technical Committee ISO/TC 38, *Textiles*, Subcommittee SC 1, *Tests for coloured textiles and colorants*.

Page 2, Subclause 2.5

Insert the following paragraph after the first paragraph of Subclause 2.5.

“The colour appearance of samples can be affected by the colour of the surround against which they are viewed and the colour of any material that is used to mask them. In order to obtain reliable test results using ISO 105-A02, the samples shall be masked with a material that is identical in colour to the sleeve that is used to mask the test strip being used. Chromatically neutral surrounds and sleeves should be used but, with proper use, grey or black sleeves are acceptable. Proper use entails that, for example, if the test strip is used with a black sleeve then the samples shall be masked using an identical black material or, if a single mask which shall be neutral in color is used, then it shall completely surround both the test strip and the samples.”

Pour plus d'infos, merci de nous contacter.

Association Sénégalaise de Normalisation

4 Avenue Jean Jaurès, Immeuble El Hadj Omar DIA, 6 ème Etage
Dakar - SENEGAL

Tel: +221 33 829 58 25

Email: asn@asn.sn