



**INTERNATIONAL STANDARD ISO 8037-2:1997**  
TECHNICAL CORRIGENDUM 1

Published 2002-11-01

INTERNATIONAL ORGANIZATION FOR STANDARDIZATION • МЕЖДУНАРОДНАЯ ОРГАНИЗАЦИЯ ПО СТАНДАРТИЗАЦИИ • ORGANISATION INTERNATIONALE DE NORMALISATION

## **Optics and optical instruments — Microscopes — Slides —**

### **Part 2:**

### **Quality of material, standard of finish and mode of packaging**

#### **TECHNICAL CORRIGENDUM 1**

*Optique et instruments d'optique — Microscopes — Lames porte-objet —*

*Partie 2: Qualité des matériaux, normes de finition et mode d'emballage*

*RECTIFICATIF TECHNIQUE 1*

Technical Corrigendum 1 to International Standard ISO 8037-2:1997 was prepared by Technical Committee ISO/TC 172, *Optics and optical instruments*, Subcommittee SC 5, *Microscopes and endoscopes*.

---

*Page 2, 3.16*

Replace the text of the note by the following:

**NOTE** For the purposes of this part of ISO 8037, the evaluation length is 60 mm for slides of 76 mm length and 30 mm for slides of 45 mm length. The evaluation length consists of one sampling length (see 4.16 of ISO 4287-1:1984).

*Page 3, 4.1.1 and 4.1.2*

Replace the text of 4.1.1 by the following:

The maximum acceptable non-flatness is 50 µm for slides of 76 mm length and 25 µm for slides of 45 mm length when measured as described in 6.11 (AQL 1.0).

Replace the second sentence of 4.1.2 by the following:

For a 45 mm slide, the thickness variation tolerance is 30 µm.

**Pour plus d'infos, merci de nous contacter.**

**Association Sénégalaise de Normalisation**

4 Avenue Jean Jaurès, Immeuble El Hadj Omar DIA, 6 ème Etage  
Dakar - SENEGAL

**Tel: +221 33 829 58 25**

**Email: [asn@asn.sn](mailto:asn@asn.sn)**